



AN ISO 9001-2008 COMPANY
Tile Fix #1

Tile Fix # 1 is a special formulation , factory prepared using carefully selected adhesives & graded raw materials for laying tiles (ceramic). Allow 12-24 hours for this screed to harden.

Add Tile Fix # 1 to water to bring it to uniform paste consistency, apply 3mm-5mm layer of Tile Fix # 1 on the uniformly leveled surface. If the surface is uniform and zero level , consumption of Tile Fix # 1 will be least. Serrate the surface with applicator provided in the bag and place tiles, pressing it firmly on Tile Fix # 1. Complete the tiling procedure in this manner.

Tile Fix #1 can be used for fixing ceramic tiles, on walls or floorings. It can be used for fixing ceramic tiles directly on mosaic tiles without hacking or removing mosaic tiles. Tile Fix #1 is most effective for wall tiles in bathrooms, kitchens, swimming pools, basements etc. Since Tile Fix #1 forms continuous impermeable layer below tiles it minimizes seepage. The specific gravity of Tile Fix #1 is in the range of 2.6. It undergoes no shrinkage on setting and hence ensures high bond strength.

Tile Fix # 1 is most suitable for kitchen tiles laying, malls, hospitals & hotels, where continuous adhesive layer of Tile Fix # 1 below tiles ensures no voids below tiles and hence eliminates algae & bacteria below tiles. This feature of Tile Adhesive is most vital for hospitals particularly I.C.U. 's, or in fact for entire hospital tiling.

For fixing very large granite slabs, marble slabs on vertical walls, use Anchorex with Tile Fix #1. Mix half Ltr Anchorex with gauging water for 20 Kgs of Tile Fix #1, mix well till paste of uniform consistency is obtained, and apply as usual. Use applicator provided with Tile Fix #1 for uniform application. Seal tile joints with our Tile Joint Sealer. Tile Fix #1 is available in 20Kgs bags.

NO	PRODUCT - DATA	
1	Consistency	Powder, Greyish, Bluish.
2	Shelf life	6 months.
3	Pot life	Use within 30 mins after mixing.
4	Packing	20 Kgs bags.
5	Coverage	40 sq.ft.per 20 kgs approximate thickness of 3-5 mm, 20 sq ft for thickness of 12-15 mm screed of tile fix.
6	Bond strength	After 24 hours 10 kgs/cm2.
7	Crushing strength	After 24 hours 40 kgs/cm2. ★
8	Application	Swimming pool tiling, tiling of bathroom toilet tiling. For Tile on Tile Applications, For hospital, hotels, kitchens etc.

It is strongly recommended that site trials be conducted using site conditions and available raw materials to evaluate the product. Since site materials and conditions are beyond our control and since above suggestions and recommendations are based on our site trials and laboratory product evaluation & trials, and since methods of use at site are beyond our control. Hence, no guarantee can either be implied or enforceable

