



RAZON ENGINEERING COMPANY PRIVATE LIMITED

660, Taboot Street, P.O.Box No.49, Pune-411001 [India] Ph:91- 20 -2613 0791, 26132217
Telefax: 91-20- 2613 0017 E-mail: razonengg@gmail.com, Web: www.razonengg.com



AN ISO 9001-2008 COMPANY

SPRMC PC 961

SPRMC PC 961 is a highly technological development, for the Ready Mix Concrete industry. Based on modified end polycarboxylates, SPRMC PC 961 is Hyper plasticizer; which enhances the workability at extremely low water content concrete, and increases the rate of hydration of the cement, so as to obtain concrete with higher strengths at all ages.

With the help of modified polycorboxylates, a very low water cement ratio is required to make flowing concrete. With optimal use of SPRMC PC self compacting concrete can be designed for pours having highly congested reinforcements or intricate shapes and designs.

The low water-cement balance enhances the compressive strength, durability; reduces porosities and possibility of carbonation. Besides, the unique technology of SPRMC PC 961 is to further increases the rate of hydration of the cement grains by enriching the cement grains with moisture; increasing the rate of cement hydration; enhancing earlier strength.

SPRMC PC 961 can facilitate high flow concrete with workability retention for placement and low vibration, if necessary. The highly fluid concrete uniformly compacts in the mould, providing a consistent, durable concrete structure.

Properties of concrete with SPRMC PC 961 :-

- **High workability of concrete at low water cement ratios**
- **Highly cohesive, non segregating concrete at low water cement ratio**
- **Very high Flow Concrete, requiring little vibration.**
- **Easy pumpability for high rise structures.**
- **Low permeability,**
- **Higher resistance to carbonation**
- **Higher bond between concrete and reinforcements**
- **Reduced shrinkage and creep**
- **High durability**
- **Higher Early strength**
- **Higher Ultimate strenght.**

Method of use:-

Dry mix the aggregates and binder, add about 80- 85% water. Add SPRMC PC 961 to this mix, and add balance water. Do not add SPRMC PC 961 to dry aggregates. The concrete must be allowed to mix on account of sufficient & necessary dispersions in low water mixes.

A test mix must be conducted to observe workability and strength characteristics.

SPRMC PC 961 may be used from a dosage of 0.7- 1.5 % by weight of binder.

SPRMC PC 961 meets the standards requirement of IS 9103:1999 /ASTM C494 type A, F & G.

No.	PRODUCT – DATA	
1	Colour	Reddish liquid
2	Consistency	Easy flowing liquid
3	Specific gravity	Approx 1.16 +/- 5%
4	pH	3-6
5	Chloride	< 1%
6	Cement Compatibility	SPRMC APC is compatible with OPC, PPC, GGBS Cement, Fly Ash and Fumed silica mixes.

OTHER PRODUCTS:-

Use **Shutter Coat 17000** for extremely clean release & demoulding

We recommend use of **CCC 102** curing compound for most effective curing of elements.

Use **P A Mortar TH-4** epoxy for high compressive / flexural strength applications.

RAZON Strextra FSX 09 developed for concrete pavement repairs- M-40 in 24 hours.

Use **Strextra R 20** for high bond strength to steel- anchoring/ grouting applications.

Coatings: Rubberised Instant Waterproof Coating • White Water Proofer • Polyurethane Coating - GHF 111 • Triple Layer Polyurethane Waterproof/ Thermal Coating • Primer Coat PU SG 104 • Top Coat PU ALK – 104 • Silver Coat PU 104 • Clear PU Lacquer (gloss) • Clear PU Lacquer (matt) • Coal Tar Epoxy CTE – 110 • Coal Tar Epoxy EP-10 • Epoxy Coating EC-111 •

Admixture: SPRMC 808 S11 B • Super Plasticizer –IWSP (M) – 101 • Super Plasticizer –IWSP (N) – 103 • Accelerator –2080 • Integral Water Proofer • IWSP –102 • I.W.P. Powder • Intrair (A.E.A) 120N • Master Plaster MP CS 101 • Block Maker BM-10 • Rapid Grout RG –117 • Tile Master TM – 1 • Anchorex 428 • Floor Hardner • Hycrete RJ – 608 • Brick Master • Super Paver • Pipe Master • Toughcrete P109 • Guniting Admixture GS-942 • Non Shrink Grout Admixture NSG A-11

It is strongly recommended that site trials be conducted using site conditions and available raw materials to evaluate the product. Since site materials and conditions are beyond our control and since above suggestions and recommendations are based on our site trials and laboratory product evaluation & trials, and since methods of use at site are beyond our control. Hence, no guarantee can either be implied or enforceable

